# 630

## Alcohol-soluble and General Polyamide Resin

**Description:** Vannu® 630 Alcohol-soluble and General Polyamide Resin is easily dissolute in alcohol. It can be dissolute in 95% dehydrated alcohol, dissolves aids the release is extremely good .It widely used in the domain such as gravure printing ink of plastic film, the flexor printing ink of plastic film domain.

| Properities | Specification | Typical Quality |
|---|---|---|
| Appearance, 25°C | Light yellow granular | OK |
| Amine number | ≤5mgKOH/g | 3mgKOH/g |
| Colour, gardner | ≤7 | 5 |
| Viscosity, 25°C | 90-150mPa.s | 120mPa.s |
| Softening Point | 115-125°C | OK |
| Acidity | ≤5mgKOH/g | 3mgKOH/g |
| Freezing Point | ≤7°C | OK |
| Package&Storage | In unopened, original containers, 12 months at 2 - 25°C, (see expiry date on original package) 25KG paper and plastic bag, etc. | |
| HS code | 3908109000 | |
| Health&Safety | Please refer to Material Safety Data Sheet | |

Shanghai Pudong Lujiazui Silver City Road 600 Lane 1
Tel: +86 21 6111 2880 Fax: +86 21 6111 2882
Email: vannu@vannu.cn
http://www.vannu.cn

Publication number [illegible] March 2012. The information and statements herein are believed to be reliable, but not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification.